

Assortments heat shrink tubing

Features:

- Crosslinked Polyolefin
- Shrink ratio: 2:1
- Flame retardant
- General purpose
- High flexibility

Application:

- Operating temperature: -55 °C to +125 °C
- Minimum shrink temperature: +70 °C
- Minimum full recovery temperature: +100 °C
- Longitudinal change: 0 ± 10% max.

Content assortment 1: 127 pcs H-2(Z) heat shrink tubing (mixed colors)

Type / Size	Length in mm	Quantity
H-2(Z) 1,6/0,8	35,0	30
H-2(Z) 2,4/1,2	35,0	25
H-2(Z) 3,2/1,6	35,0	20
H-2(Z) 4,8/2,4	35,0	20
H-2(Z) 6,4/3,2	75,0	16
H-2(Z) 9,5/4,8	75,0	8
H-2(Z) 12,7/6,4	100,0	8



Content assortment 2: 127 pcs H-2(Z) heat shrink tubing (black)

Type / Size	Length in mm	Quantity
H-2(Z) 1,6/0,8	35,0	30
H-2(Z) 2,4/1,2	35,0	25
H-2(Z) 3,2/1,6	35,0	20
H-2(Z) 4,8/2,4	35,0	20
H-2(Z) 6,4/3,2	75,0	16
H-2(Z) 9,5/4,8	75,0	8
H-2(Z) 12,7/6,4	100,0	8



Content assortment 3: 469 pcs H-2(Z) heat shrink tubing (black)

Type / Size	Length in mm	Quantity
H-2(Z) 2,4/1,2	35,0	124
H-2(Z) 3,2/1,6	35,0	100
H-2(Z) 4,8/2,4	35,0	80
H-2(Z) 6,4/3,2	35,0	60
H-2(Z) 9,5/4,8	70,0	65
H-2(Z) 12,7/6,4	70,0	15
H-2(Z) 16,0/8,0	100,0	15
H-2(Z) 19,0/9,5	70,0	5
H-2(Z) 25,4/12,7	70,0	5



H-5(3X)-F and H-5(4X)-F

Dual-wall heat shrink tubing / flexible / flame retardant / 3:1/4:1 / adhesive lined

Features:

- Crosslinked co-extruded adhesive lined Polyolefin
- Shrink ratio: 3:1 and 4:1
- Flame retardant
- Excellent sealing and insulation properties
- UV resistant

Approvals:

- UL224 125 °C VW-1 600 V file E204071
- Meets: RoHS
- Meets: SAE-AMS-DTL-23053/4

Application:

- Operating temperature: -55 °C to +125 °C
- Minimum shrink temperature: +70 °C
- Minimum full recovery temperature: +110 °C
- Longitudinal change: 0 ± 10% max.

Other information:

- Color: black
- Other colors: red, blue, yellow, green, white, transparent (flame retardant class 2)
- Also available in various lengths and in mini boxes (please see page 43)



Type / Size	As supplied: inside diameter in mm (min.)	After recovery: inside diameter in mm (max.)	After recovery: wall thickness in mm (min.)	Reel / Meter & Standard length in mm
H-5(3X)-F 3:1 3,0/1,0	3,0	1,0	1,00	150 meter
H-5(3X)-F 3:1 4,8/1,5	4,8	1,5	1,00	75 meter
H-5(3X)-F 3:1 6,0/2,0	6,0	2,0	1,00	75 meter
H-5(3X)-F 3:1 9,0/3,0	9,0	3,0	1,40	50 meter
H-5(3X)-F 3:1 12,0/4,0	12,0	4,0	1,60	30 meter
H-5(3X)-F 3:1 19,0/6,0	19,0	6,0	2,15	30 meter
H-5(3X)-F 3:1 24,0/8,0	24,0	8,0	2,40	30 meter
H-5(3X)-F 3:1 30,0/10,0	30,0	10,0	2,40	30 meter
H-5(3X)-F 3:1 40,0/13,0	40,0	13,0	2,40	30 meter
H-5(4X)-F 4:1 4,0/1,0	4,0	1,0	1,00	150 meter
H-5(4X)-F 4:1 6,0/1,5	6,0	1,5	1,00	75 meter
H-5(4X)-F 4:1 8,0/2,0	8,0	2,0	1,00	75 meter
H-5(4X)-F 4:1 12,0/3,0	12,0	3,0	1,40	50 meter
H-5(4X)-F 4:1 16,0/4,0	16,0	4,0	1,60	30 meter
H-5(4X)-F 4:1 24,0/6,0	24,0	6,0	2,15	30 meter
H-5(4X)-F 4:1 32,0/8,0	32,0	8,0	2,40	30 meter
H-5(4X)-F 4:1 52,0/13,0	52,0	13,0	2,40	1220 mm

For selecting the right type of heat shrink tubing (selection table), please see page 66
For cross references, please see page 68